



旭碳颜料级碳黑

旭碳颜料级碳黑适用于色母粒以及挤出着色和调色工艺方面的应用。

SUNBLACK (SB)系列碳黑产品完美地诠释了碳黑的关键特性：



SB910

适用于汽车内外饰以及各种家电等

SB900

适用于高浓度黑色母粒等

SB720

适用于塑料以及色母粒等

着色力强 Tint Strength

高黑度 High Jetness

呈蓝色相 Blue Undertone

高分散性 High Dispersability



ASAHI颜料级碳黑代理商

香港

裕发化工发展有限公司
香港九龙新蒲岗双喜街9-11号汇达商业中心1705室
电话:(852) 2633 2309 传真:(852) 2687 5575
网址:www.evenchem.com

华南

广州市铨发贸易有限公司
广州市东风中路445号(越秀城市广场北塔)1703房
电话:(8620) 8356 8726 传真:(8620) 8355 7703
邮编:510045

华东

铨兴发化工贸易(上海)有限公司
上海市中山南二路1007号中煌大厦1508室
电话:(8621) 6457 0569 传真:(8621) 5410 7369
邮编:200030

Grade 種別	Product Name 商品名		Particle Size 粒徑 (nm)	Surface Area 比表面積 (m ² /g)	Tinting Strength 比著色力 (%)	DBP Absorption 吸油量 (ml/100g)		Volatile Content 揮發份 (%)	pH (-)	PVC Blackness Index 黑度指數*1		Application 用途		
	Beads 粒狀品	Powder 粉狀品				Beads 粒狀	Powder 粉狀			Full Shade 濃色	Tint Shade 淡色			
HCF	SUNBLACK 900	SUNBLACK 905	15	210	150	72	80	1.5	7.5	144	106	High color carbon black - Suitable for very high blackness requirement 高級顏料碳黑 適用於需要高黑度用途。		
	SUNBLACK 910	SUNBLACK 915	14	280	140	55	65	1.5	7.5	149	95			
	SUNBLACK 930	SUNBLACK 935	13	315	140	60	66	1.5	7.5	151	91			
	SUNBLACK 960	SUNBLACK 965	14	265	150	60	70	1.5	7.5	147	107			
	SUNBLACK 970	SUNBLACK 975	14	260	150	90	98	1.5	7.5	146	108			
	—	—	—	—	—	—	—	—	—	—	—		—	
MCF	SUNBLACK 300	SUNBLACK 305	18	147	129	119	136	1.3	7.5	115	103	Medium color carbon black - Suitable for high blackness requirement resin and paint in coloring and painting applications 中級顏料碳黑 適用於需要相當黑度之樹脂及塗料的著色用途和印刷用途。		
	SUNBLACK 320	SUNBLACK 325	20	115	117	115	130	1.3	7.5	111	103			
	SUNBLACK 700	SUNBLACK 705	22	123	142	48	55	1.5	7.5	133	106			
	SUNBLACK 710	SUNBLACK 715	23	113	123	74	82	1.3	7.5	111	104			
	SUNBLACK 720	SUNBLACK 725	20	140	140	56	61	1.5	7.5	121	105			
	—	—	—	—	—	—	—	—	—	—	—		—	
	—	—	—	—	—	—	—	—	—	—	—		—	—
	—	—	—	—	—	—	—	—	—	—	—		—	—
	—	—	—	—	—	—	—	—	—	—	—		—	—
	—	—	—	—	—	—	—	—	—	—	—		—	—
RCF	SUNBLACK 200	—	26	74	99	100	—	1.3	7.5	100	100	Regular color carbon black - Suitable for general resin and paint coloring and painting ink applications. 泛用級顏料碳黑 適用於一半樹脂及塗料的著色用途和印刷油墨用途。		
	SUNBLACK 210	SUNBLACK 215	80	24	52	28	22	0.5	7.5	87	87			
	SUNBLACK 220	—	122	22	29	41	—	0.6	7.5	82	78			
	SUNBLACK 230	SUNBLACK 235	78	24	48	50	49	0.7	7.5	89	83			
	SUNBLACK 240	—	80	23	44	63	—	0.7	7.5	92	80			
	SUNBLACK 250	—	66	26	49	87	—	0.7	7.5	96	87			
	SUNBLACK 260	—	45	40	65	114	—	0.8	7.5	96	92			
	SUNBLACK 270	—	40	48	69	130	—	0.8	7.5	97	92			
	SUNBLACK 280	SUNBLACK 285	26	77	100	101	111	1.3	7.5	100	100			
	SUNBLACK 410	—	85	20	42	110	—	1.0	7.5	92	80			
—	—	—	—	—	—	—	—	—	—	—	—	—		
LFF	—	SUNBLACK X15	20	115	120	—	—	2.1	3.5	112	104	Long flow color carbon black - Good dispersibility. Suitable for high quality printing ink and paint applications, and for resin coloring applications, performing excellent flowability 良流級顏料碳黑 分散性良好，可以適用於高級印刷油墨、塗料用途以及樹脂著色用途，具有優異的流動性。		
	—	SUNBLACK X25	22	118	130	—	—	3.2	3.0	122	105			
	—	SUNBLACK X45	22	120	140	—	—	3.1	3.0	134	106			
	—	SUNBLACK X55	25	84	110	—	—	2.0	3.0	105	104			
	—	SUNBLACK X65	23	105	120	—	—	2.6	3.0	117	104			
	—	—	—	—	—	—	—	—	—	—	—		—	

*1: SUNBLACK 200 blackness index is 100 as basis 將 SUNBLACK 200 黑度指數訂為 100 當作基準表示。