



BAEROPAN MC 8890 KA/2

产品说明 类 型 : 钙/锌复合稳定剂
 外 观 : 白色粉状

使用说明 BAEROPAN R 8890 KA/2 是高效能的，以钙锌为基础的电线电缆用热稳定剂。

BAEROPAN R 8890 KA/2 特别为汽车用电线电缆而开发，符合 ISO 6722: 2002 公路车辆 – 60V & 600V Single Core Cable, C类的标准。而且 BAEROPAN R 8890 KA/2 也适合生产 105°C/125°C 的电线电缆。

在热稳定性、耐热老化、流变性能、机械性能及绝缘性方面，BAEROPAN R 8890 KA/2 与二碱式邻苯二甲酸铅的性能相当。

BAEROPAN R 8890 KA/2 的用量视具体配方、加工条件及制品要求而定，推荐用量为 8.0–15.0 phr。

基于现有的生产设备，为了优化物料的流变性能，可能需要添加适量的内、外润滑剂。

处 理 如果需要，我们可以提供材料的安全数据资料。

储 存 常温下干燥保存，如果打开使用，请注意密封。

BFE 03/2006

NOTICE: Although the information and recommendations contained in this document (hereinafter "Information") are presented in good faith and believed to be correct at the date of their publication, BAERLOCHER makes no representations or warranties as to the completeness or accuracy of Information.

Information is supplied upon the condition that the persons or entities receiving same will make their own determination as to its suitability for their purposes prior to their use. In no event, will BAERLOCHER be responsible or liable for any loss of profits, lost goodwill, direct, special, indirect, incidental, or consequential damages of any nature whatsoever, including without limitation lost revenue, resulting from the use of or reliance upon Information or the product to which Information refers.

Nothing contained in this disclaimer is to be construed as a recommendation to use any product, process, equipment or formulation in conflict with any patent or intellectual property right, and BAERLOCHER makes no representation or warranty, express or implied, that the use thereof will not infringe any patent or intellectual property rights.

No representations or warranties, either express or implied, of merchantability, fitness for a particular purpose or of any other nature are made hereunder with respect to Information or the product to which Information refers.