



BAERLOCHER GmbH
Fresinger Straße 1, D-85716
Unterschleißheim, Germany
Telefon: (49) 89 14373-0
Fax: (49) 89 14373-377/312

BAEROPAN MC 9562 KA

PVC Stabilisers

Description *	Type : Ca/Zn stabiliser Appearance : Pale yellowish powder
Application	<p>BAEROPAN MC 9562 KA is a highly efficient, non-toxic stabiliser developed particularly for the manufacture of flexible and semi-rigid, transparent and pigmented calendered film and sheet. Further applications are extrusion and injection moulding as well as powder moulding.</p> <p>Because of its good low fogging properties, BAEROPAN MC 9562 KA can also be used for automotive applications.</p> <p>The recommended usage level may vary, depending upon application between 1.3 - 2.0 phr.</p> <p>Processing stability and weatherability may be improved synergistically by combining with epoxy plasticiser BAEROSTAB LSA.</p>
Handling	A material safety data sheet for the safe handling of this product is available on request.
Storage	Dry storage at room temperature is recommended. Once opened, packaging should be firmly closed.

BFE 08/05

* **NOTICE:** Although the information and recommendations contained in this document (hereinafter "Information") are presented in good faith and believed to be correct at the date of their publication, BAERLOCHER makes no representations or warranties as to the completeness or accuracy of Information.

Information is supplied upon the condition that the persons or entities receiving same will make their own determination as to its suitability for their purposes prior to their use. In no event, will BAERLOCHER be responsible or liable for any loss of profits, lost goodwill, direct, special, indirect, incidental, or consequential damages of any nature whatsoever, including without limitation lost revenue, resulting from the use of or reliance upon Information or the product to which Information refers.

Nothing contained in this disclaimer is to be construed as a recommendation to use any product, process, equipment or formulation in conflict with any patent or intellectual property right, and BAERLOCHER makes no representation or warranty, express or implied, that the use thereof will not infringe any patent or intellectual property rights.

No representations or warranties, either express or implied, of merchantability, fitness for a particular purpose or of any other nature are made hereunder with respect to information or the product to which Information refers.