



## BAEROPAN MC 9659 KA

---

**Description**            Type            :    Ca/Zn stabilizer one pack  
                                 Appearance       :    Pale yellow powder

**Application**            BAEROPAN MC 9659 KA is a highly efficient stabilizer one-pack based on calcium/zinc developed for the extrusion of 70°C / 80°C cables application.

The product does not contain any external lubricants.

BAEROPAN MC 9659 KA has been developed to allow the manufacturer to adjust rheological properties according to individual needs. As lubricants, paraffin or polyethylene waxes are recommended.

Lubricants based on fatty acids should not be used as they could react with the basic components of the one-pack and so loose part of their activity.

The dosage of BAEROPAN MC 9659 KA depends on the formulation and the particular process and end use requirement.

Recommended dosage is approximately 3.0 - 6.0 phr.

*Note* May we draw your attention to the fact that using BAEROPAN MC 9659 KA may cause higher water absorption in the finished product than stabilizer/lubricant one-packs based on lead.

**Handling**                A material safety data sheet for the safe handling of this product is available on request.

**Storage**                 Dry storage at room temperature is recommended. Once opened, packaging should be firmly closed.

BFE 03/2006

---

**NOTICE:** Although the information and recommendations contained in this document (hereinafter "Information") are presented in good faith and believed to be correct at the date of their publication, BAERLOCHER makes no representations or warranties as to the completeness or accuracy of Information.

Information is supplied upon the condition that the persons or entities receiving same will make their own determination as to its suitability for their purposes prior to their use. In no event, will BAERLOCHER be responsible or liable for any loss of profits, lost goodwill, direct, special, indirect, incidental, or consequential damages of any nature whatsoever, including without limitation lost revenue, resulting from the use of or reliance upon Information or the product to which Information refers.

Nothing contained in this disclaimer is to be construed as a recommendation to use any product, process, equipment or formulation in conflict with any patent or intellectual property right, and BAERLOCHER makes no representation or warranty, express or implied, that the use thereof will not infringe any patent or intellectual property rights.

No representations or warranties, either express or implied, of merchantability, fitness for a particular purpose or of any other nature are made hereunder with respect to Information or the product to which Information refers.